



Shear Bond Strength of Acrylic Teeth to Acrylic Denture Base after Different Surface Conditioning Methods

Gajula Venu Madhav, Soundar Raj, Naveen Yadav, Ishitha Mudgal, Nidhi Mehta, Riddhi Tatwadiya

ABSTRACT

Background and Objectives: Acrylic resin ruled the dental profession for 60 years, and this success is attributed to its aesthetics, handling properties, physical and biological compatibility, its stability in oral environment and its cost effectiveness. The objective of this study is to evaluate and compare the bond strength of acrylic resin teeth treated with various conditioning materials like monomer and silane coupling agent.

Methodology: A study was carried out in which 96 samples were grouped into 3 groups with a sample size of 32 each (16 premolars, 16 molars). They were conditioned with different conditioning materials i.e monomer and silane coupling agent. Monomer, Silane coupling agent are coated on the ridge lap area before thermocycling and cured according to the manufacturer recommendations. The samples are retained from the flask; trimmed and polished. The samples are then subjected to shear bond strength using the Instron Universal Testing Machine.

Results: In the present study it was found that application of monomer increased the bond strength between acrylic teeth and denture base, when compared to the conventionally processed samples. However it was found that application of silane coupling agent further increased the shear bond strength between acrylic teeth and denture base.

Interpretations and conclusions: Within the confines of this study it is found that there was a significant improvement in the bond strength between the acrylic teeth and denture base when silane coupling agent and monomer were used as surface conditioning material. The order of shear strength of samples is control > monomer > silane coupling agent.

Keywords: Silane coupling agents, Shearbond strength, Universal testing machine, Acrylic denture teeth, Denture base resin, Bonding strength, Acrylin resin, Monomer.

How to cite this article: Madhav GV, Raj S, Yadav N, Mudgal I, Mehta N, Tatwadiya R. Shear Bond Strength of Acrylic Teeth to Acrylic Denture Base after Different Surface Conditioning Methods. *J Contemp Dent Pract* 2013;14(5):892-897.

Source of support: Nil

Conflict of interest: None declared

INTRODUCTION

Dental materials^{30,31} have been evolving with time, One such prominent and most commonly used material in today's dentistry is acrylic resin. Previously materials such as vulcanite, nitrocellulose, phenol formaldehyde, vinyl plastics and porcelain^{18,19} were used for denture base construction. Acrylic resin teeth were introduced in 1940's.^{1,2,27}

The invention of heat cured acrylic resin revolutionized the discipline of dental prosthesis to a great extent, since then the material has maintained its superiority over other materials in meeting the ideal requirements. Acrylic resin still remains the most preferred choice and the reason for the continual use is the simple processing equipment required and relatively low cost.³

In early years of what might be referred to as plastic age in dentistry researchers and experimenters used acrylic resin to fabricate denture teeth, bridges and inlays. Acrylic teeth⁹ are the most widely used artificial teeth for denture construction. Unlike porcelain teeth, they are suitable for a chemical adhesion between teeth and denture base resin for enhanced bonding.⁴

The failure of acrylic resin dentures due to fracture²⁸ has been reported to be high and the most common type of failure encountered was the debonding or failure in adhesion of teeth to the denture base.³ A survey showed that 33% of denture repairs were to restore debonded teeth.⁶

The aim of this study is to evaluate the shear bond strength⁵ between acrylic resin²⁰ teeth to denture base, after surface treatment with silane⁷ coupling agent as surface conditioning material.

The objective of this study is to improve the shear bond strength between acrylic teeth and denture base there by increasing the success rate of acrylic dentures.

Control groups	Bond strength (Newtons)	
	Min-max	Mean \pm SD
Premolar	63.50-143.50	110.02 \pm 19.77
Molar	171.20-350.00	235.54 \pm 42.35
Premolar + molar	63.50-350.00	172.77 \pm 71.57
p-value (premolar vs molar)	t = 10.743; p < 0.001**	

Monomer	Bond strength (Newtons)	
	Min-max	Mean \pm SD
Premolar	142.70-205.30	173.51 \pm 17.42
Molar	109.20-440.50	345.25 \pm 100.15
Premolar + molar	109.20-440.50	259.38 \pm 112.30
p-value (premolar vs molar)	t = 6.757; p < 0.001**	

MATERIALS AND METHODS

The study evaluates and compares the shear bond strength between two types of surface conditioning methods- monomer and silane coupling agent bonded⁸ to acrylic resin denture base and crosslinked acrylic resin teeth.

Making of Wax Models

Plastic polyvinyl chloride (PVC) rings of 10 cm height and 0.5 inch width were cut from a long pipe. The 10 cm PVC pipes were adhered to a steel base using sticky wax and sheets of modeling wax was melted and poured till the brim of the PVC pipes, care was taken to fill up all defective areas formed due to shrinking of wax.



Fig. 1: Prepared models



Fig. 2: Cured models

Preparing the Acrylic Denture Teeth

Premadent crosslinked acrylic molar and premolar teeth of were ground till the ridge lap area with a tungsten carbide bur and they were polished with a buff to obtain smooth surface.

Production of Specimens

The prepared teeth fixed in the PVC rings were filled with wax and the teeth were sealed with a hot wax spatula (Fig. 1).

The wax-tooth assemblies were positioned in the flask and dental plaster was poured up to the border of the PVC rings. The plaster was allowed to set and then a layer of cold mould seal was applied and left to dry. The remaining part of the flask was filled with a mixture of dental plaster and stone and the lid was closed and the flask was pressed (1,250 kgf) for 30 minutes.

After the plaster had set, the flask was placed in boiling water for 15 minutes for dewaxing. Next, the wax was eliminated by running hot water, complete elimination of wax was important from the PVC rings and the teeth ridge lap area as wax causes a detrimental effect in bonding and processing was done conventionally and models were retrieved (Fig. 2).

SURFACE CONDITIONING METHODS

The 2 sets of 96 teeth were divided into three groups based on the method of surface conditioning.

1. SM1 (control) : no surface conditioning



Fig. 3: Silane coupling



Fig. 4: Cured models subjected to shear failure loads on universal testing machine with the help of custom made jigs

Table 3: Comparison of bond strength (Newtons) in premolar, molar and premolar + molar in silane

Silane	Bond strength (Newtons)	
	Min-max	Mean ± SD
Premolar	176.00-298.40	230.81 ± 35.91
Molar	396.20-582.30	518.39 ± 57.96
Premolar + molar	176.00-582.00	374.61 ± 153.60
p-value (premolar vs molar)	t = 16.869; p < 0.001**	

- SM2 (monomer) : Two coats of heat cured monomer is applied over the ridge lap area and they were left to evaporate for 5 minutes.
- SM3 (silane) : Two coats of silane coupling agent (Fig. 3) was applied over the ridge lap area and they were left to evaporate for 5 minutes.

A heat polymerized acrylic resin (DPI) was mixed according to manufacturer’s instructions and packed between the denture teeth and the PVC rings. The flasks were bench pressed in a hydraulic press (1,250 kgf).

Curing Procedure

A short curing cycle was employed to cure the specimens. The Acrylizer was filled with water. The clamped flask was submerged in water at room temperature (23 ± 2°C). First the temperature of the water was raised to 74°C for one and half hour. Later the temperature of the water bath was maintained at boiling/100°C for an additional 1 hour.

On cooling the specimens were deflasked. Excess acrylic resin enveloping the necks of teeth was removed.


Failure Load Test

The prepared specimens were loaded on to Utm-instron universal testing machine facility at Tifac Composite Park, Kengeri, Bengaluru (Fig. 4). Samples were mounted on a customized JIG. Force was applied by a stainless JIG until fracture occurred. UTM cross head speed was maintained at 5mm/min. The fracture load was measured and recorded by a digital monitor in Newton for all specimens.


STATISTICAL ANALYSIS

A one-way analysis of variance (ANOVA) was used to find the significance of breaking strengths between different samples which were coated with different surface conditioning materials. Student ‘t’ test was used to find the significance of breaking strengths between sample types.


Table 1 and Graph 1 show comparative failure load values (Newton) of premolar and molar in control group, prepared with DPI heat cure denture base resin, and found to be statistically significant with p < 0.001, premolar showed a mean failure load value of 110.02 ± 19.77. Molar showed a mean failure load value of 235.54 ± 42.35, and premolar and molar showed a combined mean failure load of 172.77 ± 71.57 N.



Graph 1: Comparison of bond strength (Newtons) in premolar, molar and premolar + molar in control group



Graph 2: Comparison of bond strength (Newtons) in premolar, molar and premolar + molar in monomer



Graph 3: Comparison of bond strength (Newtons) in premolar, molar and premolar + molar in silane

Table 2 and Graph 2 show comparative failure load values (Newton) of premolar and molar in control group, prepared with DPI heat cure denture base resin, and found to be statistically significant with $p < 0.001$, premolar showed a mean failure load value of 173.51 ± 17.42 . Molar showed a mean failure load value of 345.25 ± 100.15 , and premolar and molar showed a combined mean failure load of 259.38 ± 112.30 N.

Table 3 and Graph 3 show comparative failure load values (Newton) of premolar and molar in control group, prepared with DPI heat cure denture base resin was found to be statistically significant with $p < 0.001$, premolar showed a mean failure load value of 230.81 ± 35.91 . Molar showed a mean failure load value of 518.39 ± 57.96 , and premolar and molar showed a combined mean failure load of 374.61 ± 153.60 N.

Statistical Methods

Descriptive statistical analysis has been carried out in the present study. Results on continuous measurements are presented on mean \pm SD (min-max) and results on categorical measurements are presented in number (%). Significance is assessed at 5% level of significance. Analysis of variance (ANOVA) has been used to find the significance of study parameters between three or more groups of patients, posthoc test has been used to find the significance pair wise between control, monomer and silane Student t-test (two tailed, independent) has been used to find the significance of study parameters on continuous scale between two groups.³¹⁻³⁴

1. Analysis of variance: F test for K population means

Objective: To test the hypothesis that K samples from K population with the same mean.

Limitations: It is assumed that population are normally distributed and have equal variance. It is also assumed that samples are independent of each other.

Method: Let the j^{th} sample contain n_j elements ($j = 1, 2, \dots, K$). Then the total number of elements is:

$$N = \sum n_j \sum \frac{x_{ij}}{n_j}$$

$$S_1^2 = \frac{\sum \sum_{i=1}^{n_1} (x_{i1} - \bar{x}_{.1})^2}{N - K} \quad S_2^2 = \frac{\sum_{i=1}^{n_1} n_j (x_{.j} - \bar{x}_{.j})^2}{K - 1}$$

$F = S_2^2/S_1^2$ which follows F distribution ($K - 1, N - K$)

2. Student t-test (two-tailed, independent)

$$t = \frac{(\bar{x}_1 - \bar{x}_2) - (\mu_1 - \mu_2)}{\sqrt{s^2 (1/n_1 + 1/n_2)}}$$

$$\text{Where } s^2 = \frac{(n_1 - 1) \sum_{i=1}^{n_1} (x_{i1} - \bar{x}_1)^2 + (n_2 - 1) \sum_{i=1}^{n_2} (x_{i2} - \bar{x}_2)^2}{n_1 + n_2 - 2}$$

3. Significant figures

+Suggestive significance (p-value: $0.05 < p < 0.10$)

*Moderately significant (p-value: $0.01 < p \leq 0.05$)

**Strongly significant (p-value : $p \leq 0.01$)

Statistical Software

The statistical software namely SPSS 15.0, Stata 8.0, MedCalc 9.0.1 and Systat 11.0 were used for the analysis of the data and Microsoft word and excel have been used to generate graphs, tables, etc.

DISCUSSION

Harold Vernon first introduced acrylic polymers as denture base materials¹⁰⁻¹⁴ in 1937. Dental materials have since been evolving with time. One such prominent and most commonly used material in today's dentistry is the acrylic resin, this is attributed to its esthetics, handling properties, biological, physical compatibility and its affordability in terms of cost and chemical stability in the mouth.

The failure rate of acrylic resin dentures as a result of fractures has been reported to be high, with the most common type of failure being the debonding of acrylic teeth to denture base resin. Clinically, it has been observed that denture fractures are usually found in areas which are subjected to high stresses which may be at the acrylic tooth/denture base interface or where the denture base material is thin in cross section and in the midline. There is a lack of bond between untreated acrylic teeth and acrylic resin denture base materials.^{2,15}

Many methods have been advocated to increase the adhesion between acrylic denture base to acrylic resin teeth. A number of precautions can be taken to reduce the incidence of debonding. Debonding may be the result of incompatible surface conditions at the tooth and denture base interface. Two factors are attributed for this is,

contamination of the surfaces and, or difference in structure of the two components due to their different processing routes.¹⁶ Both of these should be investigated because any failure will cause an increase in the cost because of repair of denture.

Studies have proved that strongest bonding to acrylic resin teeth is achieved in heat polymerized^{24,25} acrylic resin¹⁷ hence in this study denture base was fabricated using heat polymerization heat cured acrylic denture base was used in conjunction with crosslinked acrylic denture teeth.

Results from this work suggest that shear bond strength of denture teeth bonded to denture base material can be considerably enhanced by the application of suitable bonding agent. It can be postulated that the bonding agent increases the wettability of the tooth surface and may have a solvent effect, which favors a more effective diffusion of the monomers of the denture base^{22,26} polymer into the tooth.²⁶ This is in agreement with our study but this bond strength is less when compared to silane coupling agents.

This study has confirmed the findings of previous research that enhanced bonding can be achieved by the application of suitable bonding agent like monomer.²⁹ Silane coupling agent also rather than a conventionally cured denture silane coupling agent significantly increases the bond strength between the denture base and ridge lap area of the teeth when compared to monomer samples not treated with any conditioning agents.³

Hence, a simple and quick tooth chemical surface treatment could be an effective option in decreasing bonding failures and could avoid repeated denture repairs improving patient satisfaction.²⁹

CONCLUSION

- The present study evaluated the bond strength^{21,23} of acrylic teeth to the acrylic denture base²² using different surface conditioning materials like monomer and silane coupling agents.
- There was a significant improvement in the bond strength with surface conditioners.
- The order of shear bond strength of samples is control < monomer < silane coupling agent.

REFERENCES

1. Saavedra G, et al. Bond strength of acrylic teeth to denture base resin after various surface conditioning methods before and after thermocycling 2007;20(2):199-201.
2. Cunningham JL. Shear bond strength of resin teeth to heat-cured and light-cured denture base resin. *J Oral Rehabilitation* 2000;27:312-316.
3. Schoonover IC. Bonding of the plastic teeth to heat cured denture base resins. *J Am Dent Asso* 1952 March;44:285.
4. Cunningham JL, Benington IC. An investigation of the variables which may affect the bond between plastic teeth and denture base resin. *Elsevier* 1999;27:129-135.
5. Wayne Caswell C. Comparative study of the bond strength of three abrasion resistant plastic denture teeth bonded to a crosslinked and a grafted, crosslinked denture base material. *J Prost Dent* 1986 June;55(6):701.
6. Kavurt R. Examination of bond strength of resin teeth to denture base resins. *Turkey Dent J* 2005;15(4):54-61.
7. Matinlinna JP, Lassila LVJ. An introduction to silanes and their clinical applications in dentistry. *Int J Prosthodont* 2004;17(2):155-164.
8. Moffa JP. Silane bonding of porcelain denture teeth to acrylic resin denture base. *J Prosthet Dent* 1975 June;33(6):620.
9. Chung KH, Chung CY, et al. Effect of preprocessing surface treatments of acrylic teeth on bonding to the denture base. *J Oral Rehabilitation* 2007;35(4):1-8.
10. Barbosa DB, Monterio DR. Effect of monomer treatment and polymerisation methods on the bond strength of resin teeth to denture base material. *J Gerodontology* 2009;26:225-231.
11. Amin WM. Improving bonding of acrylic teeth to self-polymerising denture base resins. *Saudt Den J* 2002;14(1):15-19.
12. Cunningham JL, Benington IC. A new technique for determining. The denture tooth bond. *J Oral Rehabilitation* 1996;23:202-209.
13. Suzuki S. Adhesive bonding of denture base resins to plastic denture teeth. *J BioMed Mater Res* 1990;24:1091-1103.
14. Kawara M. Bonding of plastic teeth to denture base resins. *J Prosthet Dent* 1991;66:566-571.
15. Chung RWC. The bonding of cold cure acrylic resin to acrylic denture teeth. *The Australian Dent J* 1995;40(4):241-245.
16. Catterlin RK. Effect of tinfoil substitute contamination on adhesion of resin denture tooth to its denture base. *J Prosthetic Dent* 1993 Jan;69(1):57.
17. Marchack BW. Adhesion of denture tooth porcelain to heat polymerised denture resin. *J Prosthetic Dent* 1995;74(3):242.
18. George C, Banger P. Bonding porcelain teeth to acrylic resin denture bases. *JADA* 1967 April;74:1018.
19. Semmelman JO. Silane bonding porcelain teeth to acrylic. *JADA* 1968 Jan;76:69-73.
20. Cunningham JL. Bond strength of denture teeth to acrylic bases. *J Dent* 1993;21(5):274.
21. Huggett R. Strength of the acrylic denture base tooth bond. *Br Dent J* 1982;153:187.
22. Austin AT. Residual monomer levels in denture bases. *Br Dent J* 1982;153:424.
23. Spratley MH. An investigation of the adhesion of acrylic resin teeth to dentures. *J Prosthetic Dent* 1987 Sep;58(3):389.
24. Pekka K, Wetting V. The repair surface with methyl methacrylate affects the transverse strength of repaired heat polymerised resin. *J Prosthetic Dent* 1994 Dec;72(6):639.
25. Takashi Y. Bond strength of denture teeth to denture base resins. *Int J Prosthodontics* 2000;13(1):59.
26. Schneider RL. Tensile bond strength of acrylic resin denture teeth to a microwave or heat processed denture base. *J Prosthetic Dent* 2002;88:145-150.
27. Clancy JMS. Bond strength and failure analysis of light cured denture resins bonded to denture teeth. *J Prosthetic Dent* 1991 Feb;65(2):315.
28. Darber UR. Denture fracture—a survey. *Br Dent J* 1994;176:342-343.

29. Suliman AHA. Effects of surface treatment and bonding agents on bond strength of composite resin to porcelain. *J Prosthet Dent* 1993;70:118.
30. Craig RC. Restorative dental materials. 9th edition. CV Mosby Co. St Louis 1985.p.514-545.
31. Anusavice PKJ. Science of Dental Materials. 11th edition. Elsevier Publication. 2003.p.237-273.
32. Rosner B. Fundamentals of Biostatistics. 5th edition. Duxbury. 2000. p. 80-240.
33. Reddy MV. Statistics for Mental Health Care Research. Nimhans Publication: India. 2002:108-144.
34. Rao PSSS, Richard J. An Introduction to Biostatistics. A manual for students in health sciences. New Delhi: Prentice Hall of India 2006;86-160.

ABOUT THE AUTHORS

Gajula Venu Madhav (Corresponding Author)

Senior Lecturer, Department of Prosthodontics, Mamata Dental College, Khammam, Andhra Pradesh, India, e-mail: gajulavenumadhav@gmail.com

Soundar Raj

Professor, Department of Prosthodontics, Government Dental College and Hospital, Bengaluru, Karnataka, India

Naveen Yadav

Professor, Department of Prosthodontics, People's Dental Academy Bhopal, Madhya Pradesh, India

Ishitha Mudgal

Postgraduate Student, Department of Prosthodontics, People's Dental Academy, Bhopal, Madhya Pradesh, India

Nidhi Mehta

Postgraduate Student, Department of Prosthodontics, People's Dental Academy, Bhopal, Madhya Pradesh, India

Riddhi Tatwadiya

Postgraduate Student, Department of Prosthodontics, People's Dental Academy, Bhopal, Madhya Pradesh, India